

EVA RESIN, POLYMER-E[®] 百利滿-E[®]

乙烯醋酸乙烯酯共聚合樹脂

Ethylene Vinyl Acetate Copolymer Resins

EV102



特性

EV102 是一種乙烯醋酸乙烯酯共聚合樹脂，具有很多優異特性，包括：柔軟而有彈性，透明、無毒，抗外界應力龜裂性很強，抗衝擊强度高，低溫柔軟性很好，以及加工容易等，所以可用以開發新用途，及替代軟質 PVC、橡膠與其他彈性材料。**EV102** 可添加發泡劑、交聯劑及無機填充物，以射出或壓縮成型法製造發泡中底。

膜片擠壓加工，如鑄膜擠壓及共擠壓的成品，可作醫療與醫藥材料的特殊包裝，及食品的裹包與包裝之用。

Characteristics

POLYMER-E[®] EV102 is the ethylene vinyl acetate copolymer resin (EVA), possessing many excellent characteristics including flexibility, elasticity, transparency, non-toxicity, good resistance to environmental stress cracking, low temperature flexibility, easy processability and etc. For these characteristics, The **POLYMER-E[®] EV102** can be used to develop the new applications and replace the flexible PVC, rubbers and other elastomers. One of the applications is the incorporation of foaming agents, crosslinking agents and inorganic fillers with **POLYMER-E[®] EV102** for injection and compression molding of foamed mid-sole material for shoes. **POLYMER-E[®] EV102** is extruded to sheet such as casting and co-extrusion for special packaging of hospital and medical materials, food packaging and other packaging.

應用

1. 鞋材發泡

Applications

1. Shoe sole foaming

物理性質 Physical Properties

項目 Properties	試驗方法 Test Method	數值 Typical Value
VA 含量 VA Content (%)	APC	14
密度 Density (g/cm ³)	ASTM D1505	0.937
熔融指數 Melt Index (g/10min)	ASTM D1238	1.5
斷裂點抗張強度(模片) Tensile Strength at Break (Molded) (kg/cm ²)	ASTM D638	200
斷裂點伸長率(模片) Ultimate Elongation at Break (Molded) (%)	ASTM D638	700
抗低溫脆裂性 Low Temperature Brittleness (°C/F50)	ASTM D746	<-70
衛氏軟化溫度 Vicat Softening Point (°C)	ASTM D1525	73
熔點 Melting Point (°C)	DSC	92
硬度(蕭氏 A) Hardness (Shore A)	ASTM D2240	93

據本公司所知，上述資料應屬正確無誤，惟因使用時之情況非受本公司管制，所以本公司對上述所作之一切建議，恕不負保證之責。The information contained herein is, to our best knowledge, true and accurate. However, since conditions of use are beyond our control, all risks of such use are assumed by users.

Asia Polymer Corporation 亞洲聚合股份有限公司

Tel:886-2-87516888 Fax:886-2-26599502 Web:www.apc.com.tw

Address:12th Floor, No.37 Ji Hu Road, Nei Hu District, Taipei 114, Taiwan 地址:台北市 114 內湖區基湖路 37 號 12 樓