

EVA RESIN, POLYMER-E® 百利滿-E®

乙烯醋酸乙烯酯共聚合樹脂

Ethylene Vinyl Acetate Copolymer Resins

V33071



特性

V33071 是一種乙烯醋酸乙烯酯共聚合樹脂，具有很多優異特性，包括：柔軟而有彈性，透明，無毒，抗外界應力龜裂性很強，抗衝擊强度高，低溫柔軟性很好，以及加工容易等。

V33071 可添加發泡劑、交聯劑及無機填充物，以射出成型或模壓法製造交聯發泡鞋材。

Characteristics

POLYMER-E® V33071 is the ethylene vinyl acetate copolymer resin (EVA), possessing many excellent characteristics including flexibility, elasticity, transparency, non-toxicity, good resistance to environmental stress cracking, low temperature flexibility, good processability, etc.

One of the applications is the incorporation of foaming agents, crosslinking agents and inorganic fillers with **POLYMER-E® V33071** for injection and compression molding of shoe sole foam..

應用

1. 鞋材發泡
2. 射出發泡
3. 一般摻合應用
4. 電線電纜摻合樹脂

Applications

1. Shoe Sole Foam
2. Injection Foam
3. General Compounding
4. Wire and Cable Compounds

物理性質 Physical Properties

項 目 Properties	試 驗 方 法 Test Method	數 值 Typical Value
VA 含量 VA Content (%)	APC	33
密度 Density (g/cm ³)	ASTM D1505	0.958
熔融指數 Melt Index (g/10min)	ASTM D1238	7.5
斷裂點抗張強度(模片) Tensile Strength at Break (Molded) (kg/cm ²)	ASTM D638	100
斷裂點伸長率 (模片) Ultimate Elongation at Break (Molded) (%)	ASTM D638	1130
衛氏軟化溫度 Vicat Softening Point (°C)	ASTM D1525	-
熔點 Melting Point (°C)	DSC	63
硬度(蕭氏 A) Hardness (Shore A)	ASTM D2240	67

據本公司所知，上述資料應屬正確無誤，惟因使用時之情況非受本公司管制，所以本公司對上述所作之一切建議，恕不負保證之責。The information contained herein is, to our best knowledge, true and accurate. However, since conditions of use are beyond our control, all risks of such use are assumed by users.

Asia Polymer Corporation 亞洲聚合股份有限公司

Tel:886-2-87516888 Fax:886-2-26599502 Web:www.apc.com.tw

Address:12th Floor, No.37 Ji Hu Road, Nei Hu District, Taipei 114, Taiwan 地址:台北市 114 內湖區基湖路 37 號 12 樓